



Zytel® ST801A NC010A

NYLON RESIN

Zytel® ST801A NC010A is an Unreinforced, Super Toughened, partially UV stabilized, Polyamide 66

Product information

Resin Identification	PA66-HI	ISO 1043
Part Marking Code	>PA66-HI<	ISO 11469
ISO designation	ISO 16396-PA66-I,,M1G1NR,S12-020	

Rheological properties

	dry/cond.		
Viscosity number	130/*	cm ³ /g	ISO 307, 1157, 1628
Moulding shrinkage, parallel	1.8/-	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.4/-	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile Modulus	2000/900	MPa	ISO 527-1/-2
Stress at 50% strain	49/44	MPa	ISO 527-1/-2
Strain at break	>50/>50	%	ISO 527-1/-2
Flexural Modulus	1800/700	MPa	ISO 178
Tensile creep modulus, 1h	*/800	MPa	ISO 899-1
Tensile creep modulus, 1000h	*/700	MPa	ISO 899-1
Charpy impact strength, 23°C	-/N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	70/100 ^[P]	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	20/20	kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	80/90	kJ/m ²	ISO 180/1A
Izod notched impact strength, -30°C	15/15	kJ/m ²	ISO 180/1A
Izod notched impact strength, -40°C	20/17	kJ/m ²	ISO 180/1A
Poisson's ratio	0.4/0.45	-	

[P]: Partial Break

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	262/*	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	75/-	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.8 MPa	63/*	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	157/*	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h, 50N	205/*	°C	ISO 306
CLTE, Parallel, -40-23°C	110/*	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, parallel	140/*	E-6/K	ISO 11359-1/-2
CLTE, Parallel, 23-55°C(73-130°F)	140/-	E-6/K	ASTM E 831
CLTE, Parallel, 55-160°C	160/*	E-6/K	ISO 11359-1/-2
CLTE, Normal, -40-23°C	110/*	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	130/*	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, Normal, 23-55°C (73-130°F)	130/-	E-6/K	ASTM E 831
Coeff. of linear therm. expansion, Normal, 55-160°C	130/*	E-6/K	ISO 11359-1/-2



Zytel® ST801A NC010A

NYLON RESIN

RTI, electrical, 0.75mm	125	°C	UL 746B
RTI, electrical, 1.5mm	125	°C	UL 746B
RTI, electrical, 3mm	125	°C	UL 746B
RTI, impact, 0.75mm	75	°C	UL 746B
RTI, impact, 1.5mm	75	°C	UL 746B
RTI, impact, 3mm	75	°C	UL 746B
RTI, strength, 0.75mm	85	°C	UL 746B
RTI, strength, 1.5mm	85/*	°C	UL 746B
RTI, strength, 3mm	85	°C	UL 746B

Flammability

dry/cond.

Burning Behav. at 1.5mm nom. thickn.	HB/*	class	IEC 60695-11-10
Thickness tested	1.5/*	mm	IEC 60695-11-10
UL recognition	yes/*	-	UL 94
Burning Behav. at thickness h	HB/*	class	IEC 60695-11-10
Thickness tested	0.81/*	mm	IEC 60695-11-10
UL recognition	yes/*	-	UL 94
Oxygen index	20/*	%	ISO 4589-1/-2
FMVSS Class	B	-	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	<80	mm/min	ISO 3795 (FMVSS 302)
Hot Wire Ignition, 1.5mm	15/*	s	UL 746A
Hot Wire Ignition, 3mm	20/*	s	UL 746A

Electrical properties

dry/cond.

Relative permittivity, 100Hz	3.5/5.9	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.3/3.5	-	IEC 62631-2-1
Dissipation factor, 100Hz	50/1580	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	100/380	E-4	IEC 62631-2-1
Volume resistivity	>1E13/8.7E10	Ohm.m	IEC 62631-3-1
Surface resistivity	*/1E12	Ohm	IEC 62631-3-2
Electric strength	25/-	kV/mm	IEC 60243-1
Comparative tracking index	600/-	-	IEC 60112
Electric Strength, Short Time, 2mm	25/26	kV/mm	IEC 60243-1
High Amperage Arc Ignition Resistance, 1.5 mm	200/* ^[1]	arcs	UL 746A
High Amperage Arc Ignition Resistance, 3 mm	200/* ^[1]	arcs	UL 746A

[1]: >200

Other properties

dry/cond.

Humidity absorption, 2mm	2/*	%	Sim. to ISO 62
Water absorption, 2mm	6.5/*	%	Sim. to ISO 62
Density	1070/-	kg/m ³	ISO 1183
Water Absorption, Immersion 24h	1.1/*	%	Sim. to ISO 62



Zytel® ST801A NC010A

NYLON RESIN

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	290 °C
Min. melt temperature	280 °C
Max. melt temperature	300 °C
Max. screw tangential speed	0.3 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	50 °C
Max. mould temperature	100 °C
Hold pressure range	50 - 100 MPa
Hold pressure time	4 s/mm
Ejection temperature	190 °C

Characteristics

Additives


Release agent



Zytel® ST801A NC010A

NYLON RESIN

Viscosity-shear rate






Zytel® ST801A NC010A

NYLON RESIN

Shearstress-shear rate



Zytel® ST801A NC010A

NYLON RESIN

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass), 23°C
- ✓ Citric Acid solution (10% by mass), 23°C
- ✓ Lactic Acid (10% by mass), 23°C
- ✗ Hydrochloric Acid (36% by mass), 23°C
- ✗ Nitric Acid (40% by mass), 23°C
- ✗ Sulfuric Acid (38% by mass), 23°C
- ✗ Sulfuric Acid (5% by mass), 23°C
- ✗ Chromic Acid solution (40% by mass), 23°C

Bases

- ✗ Sodium Hydroxide solution (35% by mass), 23°C
- ✓ Sodium Hydroxide solution (1% by mass), 23°C
- ✓ Ammonium Hydroxide solution (10% by mass), 23°C

Alcohols

- ✓ Isopropyl alcohol, 23°C
- ✓ Methanol, 23°C
- ✓ Ethanol, 23°C

Hydrocarbons

- ✓ n-Hexane, 23°C
- ✓ Toluene, 23°C
- ✓ iso-Octane, 23°C

Ketones

- ✓ Acetone, 23°C

Ethers

- ✓ Diethyl ether, 23°C

Mineral oils

- ✓ SAE 10W40 multigrade motor oil, 23°C
- ✗ SAE 10W40 multigrade motor oil, 130°C
- ✗ SAE 80/90 hypoid-gear oil, 130°C
- ✓ Insulating Oil, 23°C

Standard Fuels

- ✓ ISO 1817 Liquid 1 - E5, 60°C
- ✓ ISO 1817 Liquid 2 - M15E4, 60°C
- ✓ ISO 1817 Liquid 3 - M3E7, 60°C
- ✓ ISO 1817 Liquid 4 - M15, 60°C
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✗ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✗ Diesel fuel (pref. ISO 1817 Liquid F), >90°C



Zytel® ST801A NC010A

NYLON RESIN

Salt solutions

- ✓ Sodium Chloride solution (10% by mass), 23°C
- ✗ Sodium Hypochlorite solution (10% by mass), 23°C
- ✓ Sodium Carbonate solution (20% by mass), 23°C
- ✓ Sodium Carbonate solution (2% by mass), 23°C
- ✗ Zinc Chloride solution (50% by mass), 23°C

Other

- ✓ Ethyl Acetate, 23°C
- ✗ Hydrogen peroxide, 23°C
- ✗ DOT No. 4 Brake fluid, 130°C
- ✗ Ethylene Glycol (50% by mass) in water, 108°C
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23°C
- ✓ 50% Oleic acid + 50% Olive Oil, 23°C
- ✓ Water, 23°C
- ✓ Water, 90°C
- ✗ Phenol solution (5% by mass), 23°C

Symbols used:

- ✓ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
- ✗ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.