



Rynite® 940E BK505

THERMOPLASTIC POLYESTER RESIN

Common features of Rynite® thermoplastic polyester include mechanical and physical properties such as excellent balance of strength and stiffness, dimensional stability, creep resistance, heat resistance, high surface gloss and good inherent electrical properties at elevated temperature. It can be processed over a broad temperature range and has excellent flow properties.

Rynite® thermoplastic polyester resins are typically used in demanding applications in the automotive, electrical and electronics, appliances where they successfully replace metals and thermosets, as well as other thermoplastic polymers.

Rynite® 940E BK505 is a 40% mica/glass reinforced modified polyethylene terephthalate resin with low warpage, high stiffness and strength, and excellent electrical properties.

Product information

Resin Identification	PET-(GF+MD)40	ISO 1043
Part Marking Code	>PET-(GF+MD)40<	ISO 11469

Rheological properties

Moulding shrinkage, parallel	0.2 %	ISO 294-4, 2577
Moulding shrinkage, normal	0.7 %	ISO 294-4, 2577

Typical mechanical properties

Tensile Modulus	12500 MPa	ISO 527-1/-2
Stress at break	110 MPa	ISO 527-1/-2
Strain at break	1.8 %	ISO 527-1/-2
Flexural Modulus	13000 MPa	ISO 178
Charpy impact strength, 23°C	35 kJ/m ²	ISO 179/1eU
Charpy impact strength, -40°C	35 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	7 kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -40°C	6 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.33 -	

Thermal properties

Melting temperature, 10°C/min	250 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	220 °C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	241 °C	ISO 75-1/-2
CLTE, Parallel, -40-23°C	22 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, parallel	15 E-6/K	ISO 11359-1/-2
CLTE, Parallel, 55-160°C	6 E-6/K	ISO 11359-1/-2
CLTE, Normal, -40-23°C	54 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	60 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, Normal, 55-160°C	84 E-6/K	ISO 11359-1/-2



Rynite® 940E BK505

THERMOPLASTIC POLYESTER RESIN

Flammability

FMVSS Class	B -	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	<80 mm/min	ISO 3795 (FMVSS 302)

Electrical properties

Relative permittivity, 100Hz	4.2 -	IEC 62631-2-1
Relative permittivity, 1MHz	3.9 -	IEC 62631-2-1
Dissipation factor, 100Hz	70 E-4	IEC 62631-2-1
Dissipation factor, 1MHz	146 E-4	IEC 62631-2-1
Volume resistivity	1E13 Ohm.m	IEC 62631-3-1
Surface resistivity	1E14 Ohm	IEC 62631-3-2
Electric strength	33 kV/mm	IEC 60243-1
Comparative tracking index	250 -	IEC 60112

Other properties

Density	1640 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Recommended	yes
Drying Temperature	120 °C
Drying Time, Dehumidified Dryer	4 - 6 h
Processing Moisture Content	≤0.02 ^[1] %
Melt Temperature Optimum	285 °C
Min. melt temperature	280 °C
Max. melt temperature	300 °C
Max. screw tangential speed	0.2 m/s
Mold Temperature Optimum	110 °C
Min. mould temperature	100 °C
Max. mould temperature	120 ^[2] °C
Hold pressure range	≥80 MPa
Hold pressure time	4 s/mm
Back pressure	As low as possible MPa
Ejection temperature	170 °C

[1]: At levels above 0.02%, strength and toughness will decrease, even though parts may not exhibit surface defects.

[2]: (6mm - 1mm thickness)

Characteristics

Additives	Release agent
-----------	---------------



Rynite® 940E BK505

THERMOPLASTIC POLYESTER RESIN

Revised: 2020-04-02

Page: 3 of 3

dupont.com

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

© 2021 DuPont. All rights reserved.