



# Delrin® 570 NC000

## ACETAL RESIN

Common features of Delrin® acetal resins include mechanical and physical properties such as high mechanical strength and rigidity, excellent fatigue and impact resistance, as well as resistance to moisture, gasoline, lubricants, solvents, and many other neutral chemicals. Delrin® acetal resins also have excellent dimensional stability and good electrical insulating characteristics. They are naturally resilient, self-lubricating, and available in a variety of colors and speciality grades.

Delrin® acetal resin typically is used in demanding applications in the automotive, domestic appliances, sports, industrial engineering, electronics, and consumer goods industries.

Delrin® 570 is a medium viscosity acetal homopolymer containing 20% glass fiber filler for injection moulding. It has very high stiffness, low warpage, and good creep resistance for superior performance at elevated temperature.

### Product information

Resin Identification	POM-GF20	ISO 1043
Part Marking Code	>POM-GF20<	ISO 11469

### Rheological properties

Melt volume-flow rate	7 cm <sup>3</sup> /10min	ISO 1133
Temperature	190 °C	ISO 1133
Load	2.16 kg	ISO 1133
Moulding shrinkage, parallel	1.8 %	ISO 294-4, 2577
Moulding shrinkage, normal	1.2 %	ISO 294-4, 2577

### Typical mechanical properties

Tensile Modulus	4900 MPa	ISO 527-1/-2
Stress at break	53 MPa	ISO 527-1/-2
Strain at break	12 %	ISO 527-1/-2
Flexural Modulus	4600 MPa	ISO 178
Charpy impact strength, 23°C	54 kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	50 kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	3.5 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	3 kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, 23°C	6 kJ/m <sup>2</sup>	ISO 180/1A
Ball indentation hardness, H 961/30	160 MPa	ISO 2039-1
Poisson's ratio	0.35 -	

### Thermal properties

Melting temperature, 10°C/min	178 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	125 °C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	165 °C	ISO 75-1/-2
Vicat softening temperature, 50°C/h, 50N	160 °C	ISO 306

# Delrin® 570 NC000

## ACETAL RESIN

Coeff. of linear therm. expansion, parallel	60 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	85 E-6/K	ISO 11359-1/-2
RTI, electrical, 1.5mm	105 °C	UL 746B
RTI, electrical, 3mm	105 °C	UL 746B
RTI, electrical, 6mm	105 °C	UL 746B
RTI, impact, 1.5mm	85 °C	UL 746B
RTI, impact, 3mm	85 °C	UL 746B
RTI, impact, 6mm	85 °C	UL 746B
RTI, strength, 1.5mm	90 °C	UL 746B
RTI, strength, 3mm	90 °C	UL 746B
RTI, strength, 6mm	90 °C	UL 746B

### Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	IEC 60695-11-10
Thickness tested	1.5 mm	IEC 60695-11-10
UL recognition	yes -	UL 94
Burning Behav. at thickness h	HB class	IEC 60695-11-10
Thickness tested	3 mm	IEC 60695-11-10
UL recognition	yes -	UL 94
Glow Wire Flammability Index, 3mm	600 °C	IEC 60695-2-12
FMVSS Class	B -	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	53 mm/min	ISO 3795 (FMVSS 302)

### Electrical properties

Relative permittivity, 100Hz	3.9 -	IEC 62631-2-1
Relative permittivity, 1MHz	3.9 -	IEC 62631-2-1
Dissipation factor, 1MHz	50 E-4	IEC 62631-2-1
Volume resistivity	1E13 Ohm.m	IEC 62631-3-1
Surface resistivity	>1E15 Ohm	IEC 62631-3-2
Comparative tracking index	600 -	IEC 60112

### Other properties

Humidity absorption, 2mm	0.1 %	Sim. to ISO 62
Water absorption, 2mm	0.8 %	Sim. to ISO 62
Density	1560 kg/m <sup>3</sup>	ISO 1183

### VDA Properties

Fogging, G-value (condensate)	0.5 mg	ISO 6452
-------------------------------	--------	----------

# Delrin<sup>®</sup> 570 NC000

## ACETAL RESIN

### Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	215 °C
Min. melt temperature	210 °C
Max. melt temperature	220 °C
Max. screw tangential speed	0.3 m/s
Mold Temperature Optimum	90 °C
Min. mould temperature	80 °C
Max. mould temperature	100 °C
Hold pressure range	80 - 100 MPa
Hold pressure time	8 s/mm
Annealing time, optional	30 min/mm
Annealing temperature	160 °C

### Characteristics

Additives

Release agent

### Additional Information

Injection molding

Drying is recommended, but not necessary for newly opened packaging stored in a dry location.

Follow the drying guidelines above in the following cases:


- If moisture is above the Processing Moisture Content recommendation,
- When a resin container is damaged,
- When the material is not properly stored in a dry place at room temperature, or
- When packaging stays open for a significant time.



# Delrin<sup>®</sup> 570 NC000

ACETAL RESIN

Viscosity-shear rate






# Delrin<sup>®</sup> 570 NC000

ACETAL RESIN

Shearstress-shear rate






# Delrin<sup>®</sup> 570 NC000

ACETAL RESIN

## Stress-strain






# Delrin<sup>®</sup> 570 NC000

ACETAL RESIN


## Secant modulus-strain



# Delrin<sup>®</sup> 570 NC000

ACETAL RESIN

Specific volume-temperature (pvT)








# Delrin<sup>®</sup> 570 NC000

ACETAL RESIN

## Tensile modulus-temperature



Revised: 2021-02-10

Page: 9 of 9

[dupont.com](http://dupont.com)

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

**CAUTION:** Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.

DuPont<sup>™</sup>, the DuPont Oval Logo, and all trademarks and service marks denoted with <sup>™</sup>, <sup>SM</sup> or <sup>®</sup> are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

© 2021 DuPont. All rights reserved.