



Crastin® LW9030FR BK851

THERMOPLASTIC POLYESTER RESIN

Common features of thermoplastic polyester resin include mechanical and physical properties such as stiffness and toughness, heat resistance, friction and wear resistance, excellent surface finishes and good colourability. Crastin® thermoplastic polyester resin has excellent electrical insulation characteristics and high arc-resistant grades are available. Many flame retardant grades have UL recognition (class V-0). Crastin® thermoplastic polyester resin typically has high chemical and heat ageing resistance.

The good melt stability of Crastin® thermoplastic polyester resin normally enables the recycling of properly handled production waste.

If recycling is not possible, DuPont recommends, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Crastin® thermoplastic polyester resin typically is used in demanding applications in the electronics, electrical, automotive, mechanical engineering, chemical, domestic appliances and sporting goods industry.

Crastin® LW9030FR BK851 is a 30% glass fiber reinforced, flame retardant polybutylene terephthalate blend for injection moulding. It has improved surface aesthetics, excellent dimensional stability and low warpage characteristics.

Product information

| | | |
|----------------------|----------------------|-----------|
| Resin Identification | PBT+ASA-GF30FR(17) | ISO 1043 |
| Part Marking Code | >PBT+ASA-GF30FR(17)< | ISO 11469 |

Rheological properties

| | | |
|----------------------------------|------------|---------------------|
| Melt mass-flow rate | 14 g/10min | ISO 1133 |
| Melt mass-flow rate, Temperature | 250 °C | ISO 1133 |
| Melt mass-flow rate, Load | 5 kg | ISO 1133 |
| Intrinsic viscosity | 0.93 - | ISO 307, 1157, 1628 |

Typical mechanical properties

| | | |
|--------------------------------------|----------------------|--------------|
| Tensile Modulus | 10200 MPa | ISO 527-1/-2 |
| Stress at break | 115 MPa | ISO 527-1/-2 |
| Strain at break | 1.7 % | ISO 527-1/-2 |
| Flexural Strength | 160 MPa | ISO 178 |
| Charpy impact strength, 23°C | 35 kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength, 23°C | 7 kJ/m ² | ISO 179/1eA |
| Izod notched impact strength, 23°C | 6 kJ/m ² | ISO 180/1A |
| Poisson's ratio | 0.34 - | |



Crastin® LW9030FR BK851

THERMOPLASTIC POLYESTER RESIN

Thermal properties

| | | |
|-------------------------------|--------|----------------|
| Melting temperature, 10°C/min | 225 °C | ISO 11357-1/-3 |
| RTI, electrical, 0.75mm | 140 °C | UL 746B |
| RTI, electrical, 1.5mm | 140 °C | UL 746B |
| RTI, electrical, 3mm | 140 °C | UL 746B |
| RTI, electrical, 6mm | 140 °C | UL 746B |
| RTI, impact, 0.75mm | 125 °C | UL 746B |
| RTI, impact, 1.5mm | 125 °C | UL 746B |
| RTI, impact, 3mm | 130 °C | UL 746B |
| RTI, impact, 6mm | 130 °C | UL 746B |
| RTI, strength, 0.75mm | 130 °C | UL 746B |
| RTI, strength, 1.5mm | 130 °C | UL 746B |
| RTI, strength, 3mm | 140 °C | UL 746B |
| RTI, strength, 6mm | 140 °C | UL 746B |

Flammability

| | | |
|--------------------------------------|-----------|----------------------|
| Burning Behav. at 1.5mm nom. thickn. | V-0 class | IEC 60695-11-10 |
| Thickness tested | 1.5 mm | IEC 60695-11-10 |
| UL recognition | yes - | UL 94 |
| Burning Behav. at thickness h | V-0 class | IEC 60695-11-10 |
| Thickness tested | 0.75 mm | IEC 60695-11-10 |
| UL recognition | yes - | UL 94 |
| Burning Behav. 5V at thickness h | 5VA class | IEC 60695-11-20 |
| Thickness tested | 2 mm | IEC 60695-11-20 |
| UL recognition | yes - | UL 94 |
| Oxygen index | 27 % | ISO 4589-1/-2 |
| Glow Wire Flammability Index, 3mm | 960 °C | IEC 60695-2-12 |
| Glow Wire Ignition Temperature, 3mm | 960 °C | IEC 60695-2-13 |
| FMVSS Class | DNI - | ISO 3795 (FMVSS 302) |

Electrical properties

| | | |
|------------------------------|-------------|---------------|
| Relative permittivity, 100Hz | 4.7 - | IEC 62631-2-1 |
| Relative permittivity, 1MHz | 4.4 - | IEC 62631-2-1 |
| Dissipation factor, 100Hz | 54 E-4 | IEC 62631-2-1 |
| Dissipation factor, 1MHz | 203 E-4 | IEC 62631-2-1 |
| Volume resistivity | >1E13 Ohm.m | IEC 62631-3-1 |
| Surface resistivity | 1E14 Ohm | IEC 62631-3-2 |
| Electric strength | 29 kV/mm | IEC 60243-1 |
| Comparative tracking index | 325 - | IEC 60112 |

Crastin® LW9030FR BK851

THERMOPLASTIC POLYESTER RESIN

Other properties

| | | |
|-----------------|------------------------|----------|
| Density | 1550 kg/m ³ | ISO 1183 |
| Density of melt | 1420 kg/m ³ | |

Injection

| | |
|---------------------------------|--------------------|
| Drying Recommended | yes |
| Drying Temperature | 120 °C |
| Drying Time, Dehumidified Dryer | 2 - 4 h |
| Processing Moisture Content | ≤0.04 % |
| Melt Temperature Optimum | 250 °C |
| Min. melt temperature | 240 °C |
| Max. melt temperature | 260 °C |
| Mold Temperature Optimum | 80 °C |
| Min. mould temperature | 30 °C |
| Max. mould temperature | 130 °C |
| Hold pressure range | ≥60 MPa |
| Hold pressure time | 3 s/mm |
| Back pressure | As low as possible |
| Ejection temperature | 170 °C |

Characteristics

| | |
|-----------|-----------------|
| Additives | Flame retardant |
|-----------|-----------------|

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass), 23°C
- ✓ Citric Acid solution (10% by mass), 23°C
- ✓ Lactic Acid (10% by mass), 23°C
- ✗ Hydrochloric Acid (36% by mass), 23°C
- ✗ Nitric Acid (40% by mass), 23°C
- ✗ Sulfuric Acid (38% by mass), 23°C
- ✗ Sulfuric Acid (5% by mass), 23°C
- ✗ Chromic Acid solution (40% by mass), 23°C

Bases

- ✗ Sodium Hydroxide solution (35% by mass), 23°C
- ✓ Sodium Hydroxide solution (1% by mass), 23°C
- ✓ Ammonium Hydroxide solution (10% by mass), 23°C

Alcohols

- ✓ Isopropyl alcohol, 23°C
- ✓ Methanol, 23°C

Crastin® LW9030FR BK851

THERMOPLASTIC POLYESTER RESIN

- ✓ Ethanol, 23°C

Hydrocarbons

- ✓ n-Hexane, 23°C
- ✓ Toluene, 23°C
- ✓ iso-Octane, 23°C

Ketones

- ✓ Acetone, 23°C

Ethers

- ✓ Diethyl ether, 23°C

Mineral oils

- ✓ SAE 10W40 multigrade motor oil, 23°C
- ✗ SAE 10W40 multigrade motor oil, 130°C
- ✗ SAE 80/90 hypoid-gear oil, 130°C
- ✓ Insulating Oil, 23°C

Standard Fuels

- ✗ ISO 1817 Liquid 1 - E5, 60°C
- ✗ ISO 1817 Liquid 2 - M15E4, 60°C
- ✗ ISO 1817 Liquid 3 - M3E7, 60°C
- ✗ ISO 1817 Liquid 4 - M15, 60°C
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✗ Diesel fuel (pref. ISO 1817 Liquid F), >90°C

Salt solutions

- ✓ Sodium Chloride solution (10% by mass), 23°C
- ✓ Sodium Hypochlorite solution (10% by mass), 23°C
- ✓ Sodium Carbonate solution (20% by mass), 23°C
- ✓ Sodium Carbonate solution (2% by mass), 23°C
- ✓ Zinc Chloride solution (50% by mass), 23°C

Other

- ✓ Ethyl Acetate, 23°C
- ✗ Hydrogen peroxide, 23°C
- ✗ DOT No. 4 Brake fluid, 130°C
- ✗ Ethylene Glycol (50% by mass) in water, 108°C
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23°C
- ✓ 50% Oleic acid + 50% Olive Oil, 23°C
- ✓ Water, 23°C
- ✗ Water, 90°C
- ✓ Phenol solution (5% by mass), 23°C

Symbols used:

- ✓ possibly resistant



Crastin® LW9030FR BK851

THERMOPLASTIC POLYESTER RESIN

Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

✘ not recommended - see explanation

Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.