



# Hytrel® SC969 NC010

## THERMOPLASTIC POLYESTER ELASTOMER

Common features of Hytrel® thermoplastic polyester elastomer include mechanical and physical properties such as exceptional toughness and resilience, high resistance to creep, impact and flex fatigue, flexibility at low temperatures and good retention of properties at elevated temperatures. In addition, it resists many industrial chemicals, oils and solvents. Special grades include heat stabilised, flame retardant, food contact compliant, blow molding and extrusion grades. Concentrates offered include black pigments, UV protection additives, heat stabilisers, and flame retardants. Hytrel® thermoplastic polyester elastomer is plasticiser free.

The good melt stability of Hytrel® thermoplastic polyester elastomer normally enables the recycling of properly handled production waste. If recycling is not possible, DuPont recommends, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations.

For disposal, local regulations have to be observed.

Hytrel® thermoplastic polyester elastomer typically is used in demanding applications in the automotive, fluid power, electrical/electronic, consumer goods, appliance and power tool, sporting goods, furniture, industrial and off-road transportation/equipment industry.

Hytrel® SC969 NC010 is a medium modulus grade with nominal hardness of 63D, contains a non-discoloring stabilizer and can be processed by various thermoplastic processing techniques. Developed for applications such as parts for the healthcare industry.

### SPECIAL CONTROL for HEALTHCARE APPLICATIONS

This product is manufactured according to Good Manufacturing Practice (GMP) principles and generally accepted in food contact applications in the USA when meeting applicable use conditions. This product is also tested against ISO 10993-5 and -11 and selected parts of USP Class VI. For details, individual compliance statements are available from your DuPont representative.

### Product information

Resin Identification	TPC-ET	ISO 1043
Part Marking Code	>TPC-ET<	ISO 11469

### Rheological properties

Melt volume-flow rate	8.5 cm <sup>3</sup> /10min	ISO 1133
Melt mass-flow rate	9 g/10min	ISO 1133
Temperature	230 °C	ISO 1133
Load	2.16 kg	ISO 1133
Moulding shrinkage, parallel	1.5 %	ISO 294-4, 2577
Moulding shrinkage, normal	1.5 %	ISO 294-4, 2577



# Hytrel® SC969 NC010

## THERMOPLASTIC POLYESTER ELASTOMER

### Typical mechanical properties

Tensile Modulus	260 MPa	ISO 527-1/-2
Stress at 5% strain	12 MPa	ISO 527-1/-2
Stress at 10% strain	15 MPa	ISO 527-1/-2
Stress at break	41 MPa	ISO 527-1/-2
Strain at break	>300 %	ISO 527-1/-2
Charpy impact strength, 23°C	N kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	120 <sup>[P]</sup> kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	25 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -40°C	15 kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, 23°C	81 kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength, -40°C	19 kJ/m <sup>2</sup>	ISO 180/1A
Poisson's ratio	0.48 -	
Brittleness temperature	-100 °C	ISO 974
Shore D hardness, 15s	58 -	ISO 48-4
Shore D hardness, max	63 -	ISO 48-4
Tear strength, parallel	150 kN/m	ISO 34-1

[P]: Partial Break

### Thermal properties

Melting temperature, 10°C/min	211 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	45 °C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	85 °C	ISO 75-1/-2
Vicat softening temperature, 50°C/h, 50N	100 °C	ISO 306
Vicat softening temperature, 50°C/h 10N	195 °C	ISO 306
Thermal conductivity of melt	0.14 W/(m K)	
Eff. thermal diffusivity	5.44E-8 m <sup>2</sup> /s	
Spec. heat capacity of melt	2160 J/(kg K)	

### Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	IEC 60695-11-10
Thickness tested	1.5 mm	IEC 60695-11-10

### Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Water absorption, 2mm	0.6 %	Sim. to ISO 62
Density	1220 kg/m <sup>3</sup>	ISO 1183
Density of melt	1040 kg/m <sup>3</sup>	



# Hytrel® SC969 NC010

## THERMOPLASTIC POLYESTER ELASTOMER

### Injection

Drying Recommended	yes
Drying Temperature	100 °C
Drying Time, Dehumidified Dryer	2 - 3 h
Processing Moisture Content	≤0.08 %
Melt Temperature Optimum	240 °C
Min. melt temperature	235 °C
Max. melt temperature	260 °C
Mold Temperature Optimum	45 °C
Min. mould temperature	45 °C
Max. mould temperature	55 °C

### Extrusion

Drying Temperature	90 - 110 °C
Drying Time, Dehumidified Dryer	2 - 3 h
Processing Moisture Content	≤0.06 %
Melt Temperature Optimum	230 °C
Melt Temperature Range	225 - 240 °C

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.