



# Hytrel® 4053FG NC010

## THERMOPLASTIC POLYESTER ELASTOMER

Common features of Hytrel® thermoplastic polyester elastomer include mechanical and physical properties such as exceptional toughness and resilience, high resistance to creep, impact and flex fatigue, flexibility at low temperatures and good retention of properties at elevated temperatures. In addition, it resists many industrial chemicals, oils and solvents. Special grades include heat stabilised, flame retardant, food contact compliant, blow molding and extrusion grades. Concentrates offered include black pigments, UV protection additives, heat stabilisers, and flame retardants. Hytrel® thermoplastic polyester elastomer is plasticiser free.

The good melt stability of Hytrel® thermoplastic polyester elastomer normally enables the recycling of properly handled production waste. If recycling is not possible, DuPont recommends, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations.

For disposal, local regulations have to be observed.

Hytrel® thermoplastic polyester elastomer typically is used in demanding applications in the automotive, fluid power, electrical/electronic, consumer goods, appliance and power tool, sporting goods, furniture, industrial and off-road transportation/equipment industry.

Hytrel® 4053FG is a low modulus high performance thermoplastic elastomer developed for applications in contact with food. It is suitable for extrusion and injection molding processes.

### FOOD CONTACT

This product is manufactured according to Good Manufacturing Practice (GMP) principles and generally accepted in food contact applications in Europe and the USA when meeting applicable use conditions. For details, individual compliance statements are available from your DuPont representative.

### Typical applications:

Hose and tubing, hose jackets, wire and cable jackets, film and sheeting, belting and seals.

### Product information

Resin Identification	TPC-ET	ISO 1043
Part Marking Code	>TPC-ET<	ISO 11469

### Rheological properties

Melt volume-flow rate	5 cm <sup>3</sup> /10min	ISO 1133
Melt mass-flow rate	5.3 g/10min	ISO 1133
Temperature	190 °C	ISO 1133
Load	2.16 kg	ISO 1133
Melt mass-flow rate, Temperature	190 °C	ISO 1133
Melt mass-flow rate, Load	2.16 kg	ISO 1133
Moulding shrinkage, parallel	0.2 %	ISO 294-4, 2577
Moulding shrinkage, normal	0.4 %	ISO 294-4, 2577



# Hytrel® 4053FG NC010

## THERMOPLASTIC POLYESTER ELASTOMER

### Typical mechanical properties

Tensile Modulus	56 MPa	ISO 527-1/-2
Stress at 5% strain	2.4 MPa	ISO 527-1/-2
Stress at 10% strain	4.1 MPa	ISO 527-1/-2
Stress at 50% strain	7.3 MPa	ISO 527-1/-2
Stress at break	26 MPa	ISO 527-1/-2
Strain at break	>300 %	ISO 527-1/-2
Tensile creep modulus, 1h	50 MPa	ISO 899-1
Tensile creep modulus, 1000h	40 MPa	ISO 899-1
Charpy impact strength, 23°C	N kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	N kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	N kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	N kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -40°C	N kJ/m <sup>2</sup>	ISO 179/1eA
Tensile notched impact strength, 23°C	230 kJ/m <sup>2</sup>	ISO 8256/1
Poisson's ratio	0.5 -	
Shore D hardness, 15s	38 -	ISO 48-4
Tear strength, parallel	110 kN/m	ISO 34-1

### Thermal properties

Melting temperature, 10°C/min	150 °C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	-50 °C	ISO 11357-1/-2
Temp. of deflection under load, 0.45 MPa	50 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	220 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	220 E-6/K	ISO 11359-1/-2
Eff. thermal diffusivity	5.44E-8 m <sup>2</sup> /s	

### Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	IEC 60695-11-10
Thickness tested	1.5 mm	IEC 60695-11-10
UL recognition	yes -	UL 94
Oxygen index	20 %	ISO 4589-1/-2
FMVSS Class	SE -	ISO 3795 (FMVSS 302)

### Electrical properties

Relative permittivity, 100Hz	5.2 -	IEC 62631-2-1
Relative permittivity, 1MHz	4.7 -	IEC 62631-2-1
Dissipation factor, 100Hz	110 E-4	IEC 62631-2-1
Dissipation factor, 1MHz	525 E-4	IEC 62631-2-1
Volume resistivity	7E10 Ohm.m	IEC 62631-3-1
Surface resistivity	2E14 Ohm	IEC 62631-3-2
Electric strength	18 kV/mm	IEC 60243-1
Comparative tracking index	600 -	IEC 60112

# Hytrel® 4053FG NC010

## THERMOPLASTIC POLYESTER ELASTOMER

### Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Water absorption, 2mm	0.7 %	Sim. to ISO 62
Density	1160 kg/m <sup>3</sup>	ISO 1183
Density of melt	1020 kg/m <sup>3</sup>	

### Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 3 h
Processing Moisture Content	≤0.08 %
Melt Temperature Optimum	180 °C
Min. melt temperature	170 °C
Max. melt temperature	190 °C
Mold Temperature Optimum	40 °C
Min. mould temperature	30 °C
Max. mould temperature	40 °C

### Extrusion

Drying Temperature	70 - 90 °C
Drying Time, Dehumidified Dryer	2 - 3 h
Processing Moisture Content	≤0.06 %
Melt Temperature Optimum	170 °C
Melt Temperature Range	165 - 180 °C

### Additional Information

Injection molding Snake Flow Test , mm

Inject press 62MPa, 1mm	80
Inject press 62MPa, 2.5mm	330
Inject press 83MPa(12,000psi), 1mm	95
Inject press 83MPa(12,000psi), 2.5mm	430

### Chemical Media Resistance

#### Other

✓ Water, 90°C

#### Symbols used:

✓ possibly resistant



# Hytrel® 4053FG NC010

## THERMOPLASTIC POLYESTER ELASTOMER

Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

**X** not recommended - see explanation

Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

**CAUTION:** Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.