

Product description

A glass fibre reinforced injection moulding grade with improved flame retardance. Flame retardant based on red phosphorus; giving outstanding electrical properties and very high stiffness and strength.

Physical form and storage

The product is supplied extensively dry in moisture-proof packaging in the form of cylindrical or flat pellets. Its bulk density is about 0,7 g/cm³. Standard packs are the special 25 kg bag and the 1000 kg bulk container (octagonal IBC= intermediate bulk container made from corrugated board with a liner bag). Subject to agreement other forms of packaging and shipment in tankers by road or rail are also possible. All containers are tightly sealed and should be opened only immediately prior to processing. To ensure that the material delivered cannot absorb moisture from the air the containers must be stored in dry rooms and always carefully sealed again after portions of material have been withdrawn. The product can be kept indefinitely in the undamaged bags. Experience has shown that product supplied in IBCs can be stored for about 3 months without any adverse effects on processing properties due to moisture absorption. Containers stored in cold rooms should be allowed to equilibrate to normal temperature so that no condensation forms on the pellets.

Product safety

In case processing is done under conditions as recommended (cf. processing data sheet) melts are thermally stable and do not generate hazards by molecular degradation or the evolution of gases and vapors. Like all thermoplastic polymers the product decomposes on exposure to excessive thermal load, e.g. when it is overheated or as a result of cleaning by burning off. Further information is available from the safety data sheet.

Safety instructions

Provide suitable exhaust ventilation at the drying process and in the area surrounding the melt outlet of processing machines.
Closed containers should only be opened in well-ventilated areas.
Ensure thorough ventilation of stores and work areas.

When incorrectly processing an unpleasant odour can be produced, especially when the recommended processing parameters are exceeded.

Check
- Moisture content of pellets
- Melt temperature
- Residence time

When there is a strong odour, immediately check processing parameters, ventilate the area well and recheck moisture content of material. If necessary stop processing and redry the material.

Any short stoppages in production, it is recommended that you inject material into the mould not purge an air shot. Any molten material drooling from the machine nozzle or hot runner nozzles can self-ignite when in open atmosphere. It is therefore advisable to dispose of purgings etc into water containers.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

Product Information

Typical values for uncoloured product at 23 °C ¹⁾	Test method	Unit	Values ²⁾
Properties			
Polymer abbreviation	-	-	PA66-GF50 FR
Density	ISO 1183	kg/m ³	1600
Viscosity number (0.5% in 96 % H ₂ SO ₄)	ISO 307, 1157, 1628	cm ³ /g	140
Water absorption, saturation in water at 23°C	similar to ISO 62	%	3.7 - 4.3
Moisture absorption, equilibrium 23°C/50% r.h.	similar to ISO 62	%	0.70 - 1.10
Processing			
Melting temperature, DSC	ISO 11357-1/-3	°C	260
MVR 275 °C/5 kg	ISO 1133	cm ³ /10min	25
Melt temperature, injection moulding/extrusion	-	°C	290 - 300
Mould temperature, injection moulding	-	°C	80 - 90
Moulding shrinkage, constrained ³⁾	-	%	0.4
Flammability (UL yellow card see attachment)			
Glow Wire Flammability Index, GWFI at d = 1,0 mm thickness	IEC 60695-2-12	°C	960
Thickness GWFI (1)	IEC 60695-2-12	mm	1
Oxygen index	ISO 4589-1/-2	%	27
Specific optical smoke density	EN ISO 5659-2: 2007	-	184
Toxicity of smoke CIT NLP acc. to CEN/TS 45545-2	NF X70-100-1/-2	-	0.36
Mechanical properties			
			dry / cond.
Tensile modulus	ISO 527-1/-2	MPa	16000 / 12000
Stress at break	ISO 527-1/-2	MPa	180 / 130
Strain at break	ISO 527-1/-2	%	2 / 3
Tensile creep modulus, 1000 h, strain <= 0.5%, 23°C	ISO 899-1	MPa	* / 5400
Flexural modulus	ISO 178	MPa	13000 / -
Charpy unnotched impact strength (23°C)	ISO 179/1eU	kJ/m ²	55 / 55
Charpy unnotched impact strength (-30°C)	ISO 179/1eU	kJ/m ²	50 / -
Charpy notched impact strength (23°C)	ISO 179/1eA	kJ/m ²	13 / 16
Charpy notched impact strength (-30°C)	ISO 179/1eA	kJ/m ²	11 / -
Izod notched impact strength (23°C)	ISO 180/A	kJ/m ²	14 / 20
Thermal properties			
HDT A (1.80 MPa)	ISO 75-1/-2	°C	250
HDT B (0.45 MPa)	ISO 75-1/-2	°C	250
Max. service temperature (short cycle operation)	-	°C	220
Temperature index at 50% loss of tensile strength after 5000 h	IEC 60216	°C	145
Temperature index at 50% loss of tensile strength after 20000 h	IEC 60216	°C	125
Coefficient of linear thermal expansion, longitudinal (23-80)°C	ISO 11359-1/-2	E-6/K	15 - 20
Coefficient of linear thermal expansion, transverse (23-80)°C	ISO 11359-1/-2	E-6/K	40 - 50
Thermal conductivity	DIN 52612-1	W/(m K)	0.35
Specific heat capacity	-	J/(kg*K)	1300
Electrical properties			
			dry / cond.
Relative permittivity (1 MHz)	IEC 60250	-	3.6 / 5
Dissipation factor (1 MHz)	IEC 60250	E-4	200 / -
Volume resistivity	IEC 60093	Ohm*m	1E13 / 1E10
Surface resistivity	IEC 60093	Ohm	* / 1E10
Comparative tracking index, CTI, test liquid A	IEC 60112	-	600
Electric strength K20/K20, (60*60*1 mm ^{^3})	IEC 60243-1	kV/mm	33 / 30

Footnotes

1) If product name or properties don't state otherwise.

2) The asterisk symbol "*" signifies inapplicable properties.

3) Test box with central gating, dimensions of base (107*47*1,5) mm, processing condition: TM = 320°C (unreinforced) or 330°C (reinforced), TW = 80°C

BASF SE

67056 Ludwigshafen, Germany

UL - Yellow Card

Component - Plastics

E41871

BASF SE

Performance Materials Europe, E-PME/NQ - H201, Ludwigshafen 67056 DE

A3X2G10, A3X3G10, A3X2G10 LF

Polyamide 66 (PA66), "Ultramid", furnished as pellets

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
NC, BK	0.40	V-2	4	1	65	65	65
NC, BK, GY	0.75	V-2	1	1	110	115	130
NC, GY	1.5	V-0	0	1	115	115	130
	3.0	V-0	0	1	115	115	130
BK	1.5	V-0, 5VA	0	1	115	115	130
	3.0	V-0, 5VA	0	1	115	115	130

Comparative Tracking Index (CTI): **0**

Inclined Plane Tracking (IPT): **-**

Dielectric Strength (kV/mm): **21**

Volume Resistivity (10⁹ohm-cm) : **13**

High-Voltage Arc Tracking Rate (HVTR): **0**

High Volt, Low Current Arc Resis (D495): **5**

Dimensional Stability (%): **0**

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1974-10-24
Last Revised: 2014-10-07

© 2016 UL LLC



IEC and ISO Test Methods

Test Name	Test Method	Units	Thickness Tested (mm)	Value
Flammability	IEC 60695-11-10, IEC 60695-11-20	Class (color)	0.40	V-2 (NC, BK)
			0.75	V-2 (NC, BK, GY)
			1.5	V-0 (NC, GY)
			3.0	V-0 (NC, GY)
			1.5	V-0, 5VA (BK)
			3.0	V-0, 5VA (BK)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m ²	-	-

© 2016 UL LLC