

Ryton® BR42B

polyphenylene sulfide

Ryton® BR42B 40% glass fiber reinforced polyphenylene sulfide compound is specially formulated to provide low coefficient of friction and

reduced wear rate for use in applications requiring low surface friction and/or wear.

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight	
Features	• Low Friction	• Wear Resistant
Uses	• Electrical/Electronic Applications	
RoHS Compliance	• RoHS Compliant	
Automotive Specifications	• CHRYSLER MS-DB-570 CPN 5100 ¹	• PSA Peugeot-Citroën SPA X62 5102
Appearance	• Natural Color	
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.76		ASTM D792
Molding Shrinkage			
Flow : 3.20 mm	0.20	%	
Across Flow : 3.20 mm	0.50	%	
Water Absorption (24 hr, 23°C)	0.020	%	ASTM D570

Mechanical

	Typical Value	Unit	Test method
Tensile Strength			
--	186	MPa	ASTM D638
--	185	MPa	ISO 527-2
Tensile Elongation (Break)	1.6	%	ASTM D638 ISO 527-2
Flexural Modulus	14500	MPa	ASTM D790 ISO 178
Flexural Strength			
--	269	MPa	ASTM D790
--	265	MPa	ISO 178
Compressive Strength	255	MPa	ASTM D695
Poisson's Ratio	0.40		
Coefficient of Friction ²			ASTM D3702
vs. Steel - Dynamic	0.32		
Wear Rate ²	1.60E-6	m/hr	ASTM D3702

Ryton® BR42B

polyphenylene sulfide

Impact	Typical Value	Unit	Test method
Notched Izod Impact			
3.18 mm	91	J/m	ASTM D256
--	9.5	kJ/m ²	ISO 180/A
Unnotched Izod Impact			
3.18 mm	750	J/m	ASTM D4812
--	40	kJ/m ²	ISO 180
Hardness	Typical Value	Unit	Test method
Rockwell Hardness			ASTM D785
M-Scale	97		
R-Scale	117		
Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed	265	°C	
CLTE			ASTM E831
Flow : -50 to 50°C	1.5E-5	cm/cm/°C	
Flow : 100 to 200°C	1.0E-5	cm/cm/°C	
Transverse : -50 to 50°C	4.0E-5	cm/cm/°C	
Transverse : 100 to 200°C	8.0E-5	cm/cm/°C	
Thermal Conductivity	0.33	W/m/K	
UL Temperature Rating	180	°C	UL 746B
Electrical	Typical Value	Unit	Test method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	22	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
25°C, 1 kHz	3.70		
25°C, 1 MHz	3.70		
Dissipation Factor			ASTM D150
25°C, 1 kHz	2.0E-3		
25°C, 1 MHz	3.0E-3		
Comparative Tracking Index (CTI)	150	V	UL 746A
Insulation Resistance ³ (90°C)	1.0E+11	ohms	
Flammability	Typical Value	Unit	Test method
Flame Rating (1.6 mm)	V-0		UL 94
Oxygen Index	48	%	ASTM D2863

Ryton® BR42B

polyphenylene sulfide

Injection	Typical Value	Unit
Drying Temperature	135 to 150	°C
Drying Time	2.0 to 4.0	hr
Rear Temperature	295 to 315	°C
Middle Temperature	305 to 325	°C
Front Temperature	315 to 345	°C
Nozzle Temperature	305 to 325	°C
Processing (Melt) Temp	320 to 330	°C
Mold Temperature	135 to 150	°C

Notes

Typical properties: these are not to be construed as specifications.

¹ CPN 5100

² Against 52100 steel; 100 hrs; 250 psi; 36 rpm; dry; ambient temperature; PV=2500

³ 95%RH, 48 hr

www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.

