

Ryton® R-7-120BL

polyphenylene sulfide

Ryton® R-7-120NA and R-7-120BL glass fiber and mineral filled polyphenylene sulfide compounds

provide good strength and low maintenance molding using conventional molding equipment.

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Glass Fiber \ Mineral	
Features	• Good Strength	
Uses	• Automotive Applications	
RoHS Compliance	• RoHS Compliant	
Automotive Specifications	• CHRYSLER MS-DB-570 CPN3243 Color: Black • FORD WSF-M4D803-A2	• GM GMP.PPS.002
Appearance	• Black	
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.99		ASTM D792
Molding Shrinkage			ISO 294-4
Across Flow : 3.20 mm	0.40	%	
Flow : 3.20 mm	0.20	%	
Water Absorption			
24 hr, 23°C	0.020	%	ASTM D570
24 hr, 23°C	0.021	%	ISO 62
Saturation, 23°C	0.13	%	Internal Method

Mechanical	Typical Value	Unit	Test method
Tensile Modulus			ISO 527-2
--	20700	MPa	
-- ¹	19600	MPa	
Tensile Strength			
--	124	MPa	ASTM D638
--	135	MPa	ISO 527-2
-- ¹	128	MPa	ISO 527-2
Tensile Elongation			
Break	0.90	%	ASTM D638
Break	0.80	%	ISO 527-2
Break ¹	1.0	%	ISO 527-2

Ryton® R-7-120BL

polyphenylene sulfide

Mechanical	Typical Value	Unit	Test method
Flexural Modulus			
--	19300	MPa	ASTM D790
--	19000	MPa	ISO 178
Flexural Strength			
--	207	MPa	ASTM D790
--	210	MPa	ISO 178
Compressive Strength	265	MPa	ASTM D695
Poisson's Ratio	0.36		ISO 527

Impact	Typical Value	Unit	Test method
Charpy Notched Impact Strength			ISO 179
--	5.6	kJ/m ²	
-- ¹	5.7	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
--	15	kJ/m ²	
-- ¹	16	kJ/m ²	
Notched Izod Impact			
3.18 mm	53	J/m	ASTM D256
--	6.0	kJ/m ²	ISO 180/A
Unnotched Izod Impact			
3.18 mm	210	J/m	ASTM D4812
--	15	kJ/m ²	ISO 180

Hardness	Typical Value	Unit	Test method
Rockwell Hardness			ASTM D785
M-Scale	101		
R-Scale	118		

Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed	265	°C	
Melting Temperature	280	°C	ISO 11357-3
CLTE			ASTM E831
Flow : -50 to 50°C	1.5E-5	cm/cm/°C	
Flow : 100 to 200°C	1.5E-5	cm/cm/°C	
Transverse : -50 to 50°C	3.0E-5	cm/cm/°C	
Transverse : 100 to 200°C	7.0E-5	cm/cm/°C	
Thermal Conductivity	0.59	W/m/K	Internal Method
UL Temperature Rating	220 to 240	°C	UL 746B

Electrical	Typical Value	Unit	Test method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength	16	kV/mm	ASTM D149

Ryton® R-7-120BL

polyphenylene sulfide

Electrical	Typical Value	Unit	Test method
Dielectric Constant			ASTM D150
25°C, 1 kHz	4.90		
25°C, 1 MHz	4.90		
Dissipation Factor			ASTM D150
25°C, 1 kHz	4.0E-3		
25°C, 1 MHz	2.0E-3		
Arc Resistance	185	sec	ASTM D495
Comparative Tracking Index (CTI)	250	V	UL 746A
Insulation Resistance ² (90°C)	1.0E+11	ohms	Internal Method

Flammability	Typical Value	Unit	Test method
Flame Rating			UL 94
0.8 mm	•	V-0	
	•	5VA	
1.6 mm	•	V-0	
	•	5VA	
Oxygen Index	61	%	ASTM D2863

Injection	Typical Value	Unit
Drying Temperature	135 to 150	°C
Drying Time	2.0 to 4.0	hr
Rear Temperature	295 to 315	°C
Middle Temperature	305 to 325	°C
Front Temperature	315 to 345	°C
Nozzle Temperature	305 to 325	°C
Processing (Melt) Temp	320 to 330	°C
Mold Temperature	135 to 150	°C

Notes

Typical properties: these are not to be construed as specifications.

¹ Conditioned data is meant to simulate 23°C 50% RH equilibrium values. Conditioning of specimens was achieved per ISO 1110 by exposing specimens for 11 days, 70°C and 62% RH.

² 95%RH, 48 hr

www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.

