

# Amodel® A-8930 HS polyphthalamide

Amodel® A-8930 HS is a 30% glass-fiber-reinforced, heat-stabilized polyphthalamide (PPA) with a high heat deflection temperature and very high tensile strength. Excellent creep resistance and low

moisture absorption are also characteristic of this resin.

- Black: A-8930 HS BK 328

## General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight	
Additive	• Heat Stabilizer	
Features	• Chemical Resistant • Creep Resistant • Good Dimensional Stability • Good Stiffness • High Heat Resistance	• High Stiffness • High Strength • High Temperature Strength • Low Moisture Absorption
Uses	• Appliances • Automotive Applications • Automotive Electronics • Connectors • Consumer Applications	• Housings • Industrial Applications • Machine/Mechanical Parts • Metal Replacement
Appearance	• Black	
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Typical Value	Unit	Test method
Density	1.47	g/cm <sup>3</sup>	ISO 1183/A
Molding Shrinkage			ASTM D955
Flow	0.45	%	
Across Flow	0.89	%	
Water Absorption (24 hr)	0.21	%	ASTM D570

Mechanical	Typical Value	Unit	Test method
Tensile Modulus (23°C)	12100	MPa	ISO 527-1
Tensile Stress (Break, 23°C)	194	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	1.8	%	ISO 527-2
Flexural Modulus (23°C)	11400	MPa	ISO 178
Flexural Strain at Break (23°C)	2.6	%	ISO 178
Flexural Strength (Break, 23°C)	288	MPa	ISO 178

# Amodel® A-8930 HS

## polyphthalamide

Impact	Typical Value	Unit	Test method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	7.5	kJ/m <sup>2</sup>	
23°C	7.9	kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	46	kJ/m <sup>2</sup>	
23°C	48	kJ/m <sup>2</sup>	
Notched Izod Impact Strength (23°C)	8.1	kJ/m <sup>2</sup>	ISO 180/A
Unnotched Izod Impact Strength			ISO 180/A
-30°C	37	kJ/m <sup>2</sup>	
23°C	43	kJ/m <sup>2</sup>	

Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	311	°C	ISO 75-2/Bf
1.8 MPa, Unannealed	290	°C	ISO 75-2/Af
Melting Temperature	323	°C	ISO 11357-3

Injection	Typical Value	Unit
Drying Temperature	120	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.030 to 0.060	%
Rear Temperature	310 to 330	°C
Middle Temperature	315 to 330	°C
Front Temperature	325 to 335	°C
Processing (Melt) Temp	320 to 345	°C
Mold Temperature	150	°C

### Injection Notes

#### Mold Temperature:

- Higher tool temperatures might be required for thin wall sections

#### Storage:

- Amodel® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Amodel® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Amodel® processing guide.

## Notes

Typical properties: these are not to be construed as specifications.

# Amodel® A-8930 HS

## polyphthalamide

---

---

**[www.syensqo.com](http://www.syensqo.com)**

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.

