

# Amodel® A-4160 HSL polyphthalamide

Amodel® A-4160 HSL resin is a 60% glass reinforced, heat stabilized polyphthalamide (PPA) which exhibits high modulus at elevated temperatures, a high heat deflection temperature and exceptional creep resistance. This material was designed for

metal replacement applications. Its rapid crystallization and good flow characteristics allow shorter cycles for enhanced molding productivity.

- Black: A-4160 HSL BK324

## General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Glass Fiber, 60% Filler by Weight	
Additive	• Heat Stabilizer • Lubricant	• Mold Release
Features	• Chemical Resistant • Creep Resistant • Fast Molding Cycle • Good Dimensional Stability • Good Toughness • Heat Stabilized	• High Heat Resistance • High Strength • Hot Water Moldability • Low CLTE • Lubricated • Ultra High Stiffness
Uses	• Automotive Applications • Automotive Electronics • Automotive Under the Hood • Camera Applications • Cell Phones • Connectors	• Electrical/Electronic Applications • Housings • Industrial Applications • Machine/Mechanical Parts • Metal Replacement • Transmission Applications
RoHS Compliance	• RoHS Compliant	
Automotive Specifications	• ASTM D6779 PA102G60	
Appearance	• Black	
Forms	• Pellets	
Processing Method	• Water-Heated Mold Injection Molding	

Physical	Typical Value	Unit	Test method
Density	1.75	g/cm <sup>3</sup>	ISO 1183/A
Molding Shrinkage			ISO 294-4
Across Flow	0.80	%	
Flow	0.50	%	
Water Absorption (24 hr, 23°C)	0.19	%	ISO 62

# Amodel® A-4160 HSL

## polyphthalamide

Mechanical	Typical Value	Unit	Test method
Tensile Modulus			ISO 527-1
23°C	23300	MPa	
200°C	8770	MPa	
Tensile Stress			ISO 527-2
Break, 23°C	244	MPa	
Break, 200°C	79.6	MPa	
Tensile Strain			ISO 527-2
Break, 23°C	1.4	%	
Break, 200°C	3.3	%	
Flexural Modulus			ISO 178
23°C	19300	MPa	
200°C	8500	MPa	
Flexural Stress			ISO 178
23°C	385	MPa	
200°C	137	MPa	

Impact	Typical Value	Unit	Test method
Charpy Notched Impact Strength (23°C)	13	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	130	kJ/m <sup>2</sup>	ISO 179/1eU

Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ISO 75-2/A
1.8 MPa, Unannealed	304	°C	

Injection	Typical Value	Unit
Drying Temperature	120	°C
Drying Time	4.0	hr
Rear Temperature	318 to 324	°C
Front Temperature	327 to 332	°C
Processing (Melt) Temp	329 to 343	°C
Mold Temperature	66 to 140	°C

### Injection Notes


Injection Pressure: 3 to 4 in/sec

### Storage:

- Amodel® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Amodel® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Amodel® processing guide.

# Amodel® A-4160 HSL polyphthalamide

## Isothermal Stress vs. Strain (ISO 11403)



# Amodel® A-4160 HSL

## polyphthalamide

---

## Notes

---

Typical properties: these are not to be construed as specifications.



---

**[www.syensqo.com](http://www.syensqo.com)**

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.