

SANTOPRENE® 101-60W261

SANTOPRENE®

A soft, black, versatile thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties and chemical resistance for use in a wide range of applications. This grade of Santoprene® TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding, extrusion or blow molding. It is polyolefin based and recyclable within the manufacturing stream.

Key Features

- Designed for applications requiring good elastic recovery
- Recommended for applications requiring excellent flex fatigue resistance

Product information

Resin Identification	TPV	ISO 1043
Part Marking Code	>TPV<	ISO 11469

Typical mechanical properties

Tensile stress at 100% elongation, perpendicular	1.9 MPa	ISO 37
Stress at break, perpendicular	7.2 MPa	ISO 527-1/-2 or ISO 37
Elongation at break, perpendicular	550 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 15s	65	ISO 48-4 / ISO 868
Compression set, 23 °C, 24h	14 %	ISO 815
Compression set, 100 °C, 24h	39 %	ISO 815

Physical/Other properties

Density	950 kg/m ³	ISO 1183
---------	-----------------------	----------

Additional information

Processing Notes

Processing Notes

Desiccant drying for 3 hours at 80 °C (180 °F) is recommended. Santoprene® TPV has a wide temperature processing window from 175 to 230 °C (350 to 450 °F) and is incompatible with acetal and PVC.