

# FORTRON® ICE 506L

## Polyphenylene sulfide

FORTRON ICE 506L is a 40% glass fiber reinforced polyphenylene sulfide of high flowability, that belongs to our new generation of Fortron® PPS. This new technology allows optimization of molding conditions with faster cycle times. Due to the faster crystallization of the material at a higher temperature, the option of mold wall temperature reduction can be subject of advanced process optimization. The potential for optimization of Fortron® ICE by cycle time reduction is possible by standard cavity surface temperatures of 140 °C. The potential for lowering the mold temperature must be checked individually and it depends on process and part design.

### Product information

Resin Identification	PPS-GF40	ISO 1043
Part Marking Code	>PPS-GF40<	ISO 11469

### Rheological properties

Moulding shrinkage, parallel	0.3 %	ISO 294-4, 2577
Moulding shrinkage, normal	0.6 %	ISO 294-4, 2577

### Typical mechanical properties

Tensile modulus	14700 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	200 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.9 %	ISO 527-1/-2
Flexural modulus	14500 MPa	ISO 178
Flexural strength	280 MPa	ISO 178
Compressive modulus	14500 MPa	ISO 604
Compressive strength	265 MPa	ISO 604
Charpy impact strength, 23 °C	53 kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30 °C	53 kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23 °C	10 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30 °C	10 kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, 23 °C	10 kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength, -30 °C	10.0 kJ/m <sup>2</sup>	ISO 180/1A
Izod impact strength, 23 °C	34 kJ/m <sup>2</sup>	ISO 180/1U
Izod impact strength, -30 °C	34 kJ/m <sup>2</sup>	ISO 180/1U
Hardness, Rockwell, M-scale	100	ISO 2039-2
Poisson's ratio	0.33 <sup>[C]</sup>	

[C]: Calculated

### Thermal properties

Melting temperature, 10 °C/min	280 °C	ISO 11357-1/-3
Glass transition temperature, 10 °C/min	90 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	270 °C	ISO 75-1/-2
Temperature of deflection under load, 8 MPa	215 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	26 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	42 E-6/K	ISO 11359-1/-2
Specific heat capacity of melt	1500 J/(kg K)	ISO 22007-4

# FORTRON® ICE 506L

## Polyphenylene sulfide

### Electrical properties

Relative permittivity, 1MHz	4.1	IEC 62631-2-1
Dissipation factor, 1MHz	20 E-4	IEC 62631-2-1
Volume resistivity	>1E13 Ohm.m	IEC 62631-3-1
Surface resistivity	>1E15 Ohm	IEC 62631-3-2
Comparative tracking index	125	IEC 60112
Arc Resistance	134 s	UL 746B

### Physical/Other properties

Water absorption, 2mm	0.02 %	Sim. to ISO 62
Water absorption, Immersion 24h	0.02 %	Sim. to ISO 62
Density	1600 kg/m <sup>3</sup>	ISO 1183

### Injection

Drying Recommended	yes
Drying Temperature	130 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.02 %
Melt Temperature Optimum	330 °C
Min. melt temperature	310 °C
Max. melt temperature	340 °C
Screw tangential speed	0.2 - 0.3 m/s
Mold Temperature Optimum	150 °C
Min. mould temperature	140 °C
Max. mould temperature	160 °C
Hold pressure range	30 - 70 MPa
Back pressure	3 MPa
Ejection temperature	240 °C

### Characteristics

Additives	Release agent, Nucleated
-----------	--------------------------

### Additional information

Processing Notes

### Pre-Drying

FORTRON should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be =< - 30° C. The time between drying and processing should be as short as possible.

### Storage

For subsequent storage the material should be stored dry in the dryer until processed (≤ 60 h).

# FORTRON® ICE 506L

Polyphenylene sulfide

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2024 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.